



TIE-COAT PRIMER

Product Information and Specifications

Tie-Coat Primer is a very tough and sandable, non-moisture sensitive single-component polyurethane primer. It contains hybrid polymeric resins which have excellent adhesion characteristics to most painted surfaces, especially that of POR-15, because we have matched and blended the isocyanate resin components of both coatings to make them fully compatible. **Tie-Coat Primer** is highly resistant to penetrating topcoats such as enamels, lacquers, and two-component finishes ("penetrating topcoats" refers to topcoats with especially aggressive solvent bases which can penetrate and ruin a partially cured base coat).

Tie-Coat Primer is not a reactive coating (as is **POR-15**, which reacts to moisture), but its revolutionary adhesion promoters make it an ideal interlocking prime coat between **POR-15** and various topcoats. It sands to a perfectly smooth finish. It may be used over well-seasoned **POR-15** coatings even if they are more than a year old, with no special preparation other than cleaning the surface.

Product Characteristics:

Boiling Point: 350-385°F / 177-196°C
Vapor Density: Heavier than air
Reactivity in water: none
Odor: Light aromatic
Viscosity: Range@77°F: 250-500 CPS
Specific Gravity (water = 1): 1.32
% Volatile by volume: 21%
Evaporation rate (Ether=1): Solvent, 4.5
Color: Bluish-Gray
Volatile organics: 2.33 lbs/gal (270 gr/ltr)
Flash point: 108°F / 42.2°C
Solubility in water: negligible
Carcinogens (or potential): none
Stability: stable under normal conditions
Conditions to avoid: Sparks, open flame
Materials to avoid: oxidizing agents
Current TLV:
ACGIH: 100 ppm TWA
Ceiling value OSHA PEL: 500

Surface Preparation: Surface to be coated should be free of grease, oil, foreign substances. Use of a scuff pad will create the best surface for adhesion.

Thinning: May be thinned up to 5% with POR-15 Solvent. Thinning is not usually required. Subsequent coats may be applied at 12 hour intervals if desired. Stir Tie-Coat thoroughly before using; do not shake as this will create air bubbles.

Pressure: Spray at approximately 35 lbs. **Do not** sand between coats of primer. Sand only after final coat of primer has fully dried (24 hours).

Topcoating: Allow a minimum of 24 hours before applying any topcoat over **Tie-Coat Primer**. Failure to allow enough dry time before applying topcoats may result in spidering or crinkling of the finish. We do not recommend topcoating **Tie-Coat Primer** with other primers prior to finish coating.

Storage & Handling: Store in tightly closed container and protect from moisture and foreign materials. Ideal storage temperature range is 50 - 81° F (10 - 27°C).

Summary:

1. Stir, do not shake, Tie-Coat Primer before using.
2. Do not sand between coats. Sand only after final coat has dried thoroughly (24 hours).
3. As with all solvent-based coatings, use an organic vapor particulate respirator, NIOSH/MSHA approved, when spraying or brushing. In closed areas, use an air-supplied respirator when spraying.